

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
21 February 2002 (21.02.2002)

PCT

(10) International Publication Number
WO 02/14066 A1

- (51) International Patent Classification⁷: **B32B 15/08**, 27/18, 27/30, 27/34, C08L 27/12, 77/00
- (74) Agents: **NIEWYK, Anthony et al.**; Baker & Daniels, Suite 800, 111 East Wayne Street, Fort Wayne, IN 46802 (US).
- (21) International Application Number: **PCT/US01/41761**
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 16 August 2001 (16.08.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/225,944 17 August 2000 (17.08.2000) US
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): **WHITFORD CORPORATION** [US/US]; P.O. Box 2347, West Chester, PA 19380 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **LEECH, Lawrence, D.** [US/US]; 1218 Brinton Circle, West Chester, PA 19380 (US). **CHUNG, Daniel, C.** [US/US]; 101 Dogwood Hill, Princeton, NJ 08540 (US). **MILLER, Michael, W.** [US/US]; 503 Pine Needle Drive, Exton, PA 19341 (US).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 02/14066 A1

(54) Title: SINGLE COAT NON-STICK COATING SYSTEM AND ARTICLES COATED WITH SAME

(57) Abstract: Single coat coating systems (22), as well as articles coated with such non-stick coating systems, are provided. The single coat system includes a fluoropolymer copolymer (14a), such as a fluoropolymer terpolymer including tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride monomers, which fluoropolymer copolymers are referred to collectively as THV. The single coat system exhibits excellent substrate adhesion and release properties, is resistant to separation failure at the interface between the binder (12) and fluoropolymer components (14a), and exhibits excellent adhesion to smooth substrates (16). The single coat system may also include a high level of fillers to provide increased damage resistance without compromising the above benefits.

Lawrence D. Leech
Daniel C. Chung
Michael W. Miller

SINGLE COAT NON-STICK COATING SYSTEM
AND ARTICLES COATED WITH SAME

BACKGROUND OF THE INVENTION

1. Field of the Invention.

The present invention relates to non-stick coating systems which are applied in single coats to the surface of a substrate to provide a coated substrate having a non-stick coating to which extraneous materials will not adhere. More particularly, the present invention relates to a single coat composition which provides excellent release properties and excellent intracoat cohesion between the binder and fluoropolymer components thereof.

2. Description of the Related Art.

Nonstick coatings have been well known for more than twenty years. These coatings combine good adhesion to substrates such as metal, glass, or ceramics, good cohesion for mechanical strength such as resistance to scratching and abrasion, and a low surface energy surface that is difficult to wet and resistant to adhesive attachment by other substances. Typically, these coatings include: 1) one or more highly fluorinated polymers for nonstick properties, e.g., polytetrafluoroethylene (PTFE), fluorinated ethylenepropylene (FEP) or perfluoroalkyl (PFA), and 2) one or more heat resistant binder resins for adhesion, e.g., polyamideimide (PAI), polyethersulfone (PES), or polyphenylene sulfide (PPS), and 3) one or more pigments and fillers for coloring or varied mechanical properties.

Nonstick coatings may be formulated for application and use in one layer or in multiple layers. In a one layer coating, all of the above requirements must be achieved in a single coat. Therefore, since both adhesion and nonstick properties must be obtained in the same layer, the result is a compromise in performance. On the other hand, in the multilayer coating, different layers provide different functions to achieve both good adhesion and mechanical strength and good nonstick or release properties. For example, a primer or first layer of a multilayer coating might contain all of the ingredients listed above, but with a high concentration of binder resin to promote adhesion, while a topcoat or top layer of a multilayered coating might contain primarily a fluoropolymer to provide the best nonstick surface. Therefore a multilayered coating with each layer specialized as to function may have

a superior balance of adhesion and release properties compared to a single layer coating where all properties must be achieved in the same layer.

Primers for multilayer coatings and one layer coatings depend upon the same mechanism of film formation to realize their specific properties. In both cases, the stratification of the ingredients is needed to increase the concentration of binder resin at the substrate to promote adhesion, and to increase the concentration of fluoropolymer resin at the surface to improve nonstick properties or to provide a surface to which subsequent coats may be bonded by sintering. Over the course of the development of such coating systems, it has come to be accepted that the adhesion of the primers to metal substrates is a function of the amount of organic binder resin present at the interface between the substrate and the coating. It is well known that organic binders, such as polyamideimide, polyether sulfone and polyphenylene sulfide, for example, have excellent adhesion to metals.

Likewise, it has come to be accepted that the adhesion of subsequent layers or coats to the primer depends upon the amount of fluoropolymer present at the interface between the primer and the next layer. This is due to the fact that adhesion between the primer and subsequent layers is achieved by the fusing or sintering of the fluoropolymer in the primer to the fluoropolymer in the subsequent layer during the curing process at temperatures above the melting point of the fluoropolymers.

A mixture of ingredients is expected, however, at both the primer-substrate and the primer topcoat interfaces, because the primers themselves include a mixture of ingredients. Some fluoropolymer will therefore be present at the primer-substrate interface, and thereby adversely affect adhesion to the substrate, and some binder will be present at the primer-topcoat interface, and thereby adversely affect the intercoat adhesion with subsequent layers. For these reasons, much development effort has been directed to achieving a greater degree of separation or stratification between the binder resin and the fluoropolymer in the primer, so that the binder moves to the bottom of the primer layer to increase substrate adhesion, and the fluoropolymer moves to the top of the primer layer to increase intercoat adhesion. Such differences in composition from top to bottom of the primer layer are known as "concentration gradients," and are described in U.S. Patent No. 4,087,394 to Concannon (1978) and in U.S. Patent No. 5,240,775 to Tannenbaum (1993).

The development of sharper concentration gradients in primers has become more important with the increased emphasis on applying non-stick multi-layered coatings to "smooth" substrates. Traditionally, metal substrates had been roughened by gritblasting or

finishing (sanding) before application of a non-stick coating thereto. Application to "smooth" substrates eliminates the slow and expensive roughening process. For purposes of the present application, a "smooth" substrate refers to a substrate that has been chemically cleaned and lightly etched to an average roughness (Ra) of less than 100 microinches (2.5 microns), and preferably of less than 50 microinches (1.25 micron). By way of comparison, untreated rolled aluminum, for example, has an average roughness of 12 - 20 microinches (0.25 - 0.50 microns), and gritblasted aluminum has an average roughness of 160 to 220 microinches (4 to 5.25 microns).

A more recent direction in the development of primers is the inclusion of hard fillers to increase scratch and damage resistance. The use of such fillers is well known, and is also disclosed in U.S. Patent No. 4,049,863 to Vassiliou (1977), noted above, in a range up to 20% by weight of the solids. More recent disclosures of the use of hard fillers may be found in U.S. Patent Nos. 5,250,356 to Batzer (1993) and 5,562,991 to Tannenbaum (1996), wherein the amount of filler used is as high as 35% by weight of the solid material.

In practice, the main raw materials used in primers for non-stick, multi-layered coatings have not changed greatly in recent years. The preferred organic binder remains a polyamideimide ("PAI") resin, prepared as an aqueous polyamic acid salt. The preferred fluoropolymer remains an aqueous dispersion of polytetrafluoroethylene ("PTFE") resin with a melt viscosity greater than 10^3 poise. The recent improvements in the performance of primers has come from (1) incrementally enhancing the original, basic mechanism for promoting substrate adhesion and intercoat adhesion, *viz.*, increasing the stratification of the primer through the addition of fluoropolymers such as fluorinated ethylene propylene ("FEP") that have lower melt viscosity and lower melting points than PTFE, and (2) adding ever increasing amounts of hard fillers for improved penetration and scratch resistance.

Adding hard fillers, while increasing the damage resistance of the primer, has the undesirable effect of adding an additional ingredient to the primer, which competes for space at the critical primer-substrate and primer-topcoat interfaces, and thereby detracts from the amount of preferred materials, as described above, which are required at the primer-substrate and primer-topcoat interfaces for maximum bonding.

Additionally, recent effort has been directed to the development of a single coat, non-stick coating system having fluoropolymer and binder components, in which stratification between the fluoropolymer and binder is allowed in order to enhance the substrate adhesion and the release properties of the coating without failure between the fluoropolymer and binder

components, and also, which coating has excellent adhesion to smooth substrates and allows the incorporation of high levels of fillers therein for improved scratch and damage resistance.

As shown in Fig. 1, compensating for this loss of bond strength by forcing greater separation/stratification of these materials has an obvious limit. In coating system 10, the stratification between binder 12 and fluoropolymer 14 of primer 22 allows binder 12 and fluoropolymer 14 to adhere well to substrate 16 and to topcoat 24, respectively. However, the large degree of stratification between binder 12 and fluoropolymer 14 actually creates, in effect, a new binder-fluoropolymer interface 20. Specifically, the mechanical interconnection between binder 12 and fluoropolymer 14 is minimal, and subject to failure, at binder-fluoropolymer interface 20. Therefore, failure of coating system 10 occurs within primer 22 itself, because the connection between the organic binder and fluoropolymer (the intracoat cohesion) is a mechanical interconnection, and prone to separation failure upon a large degree of stratification within primer 22. The same type of failure illustrated in Fig. 1 may occur in conventional single coat, non-stick coating systems which include fluoropolymer and binder components.

What is needed is a single coat, non-stick coating system which exhibits excellent substrate adhesion, yet is resistant to separation failure at the interface between the binder and fluoropolymer components of the coating.

A further need is for a single coat, non-stick coating system, including a coating which allows for the incorporation into the coating of a high level of fillers to provide increased damage resistance.

A still further need is for a single coat, non-stick coating system, including a binder which has excellent adhesion to a smooth substrate.

A still further need is for a single coat, non-stick coating having excellent substrate adhesion and release properties, yet which is resistant to separation failure at the interface between the binder and fluoropolymer components of the coating.

SUMMARY OF THE INVENTION

The present invention provides single coat, non-stick coating systems, as well as substrates coated with the non-stick coating systems. The single coat system includes a fluoropolymer, which is a polymer including a $\text{CF}_2\text{-CH}_2$ moiety in the polymer chain. An exemplary fluoropolymer is a fluoropolymer copolymer, such as a fluoropolymer terpolymer

including repeating monomers of tetrafluoroethylene ("TFE"), hexafluoropropylene ("HFP"), and vinylidene fluoride ("VDF"). Fluoropolymer copolymers including TFE, HFP, and VDF are collectively referred to as "THV". Further examples of such fluoropolymers are polyvinylidene fluoride ("PVDF") homopolymers, ethylene tetrafluoroethylene ("ETFE") and HFP/VDF bipolymers, ethylene fluorinated ethylene-propylene ("EFEP") terpolymers, and other possible combinations of ethylene and fluoroethylenic monomers.

The present inventors have found that a coating including THV may be applied to a substrate in a single coat, the coating having excellent release properties and substrate adhesion, as well as excellent intracoat cohesion, or resistance to separation failure between the fluoropolymer and binder components. Further, the single coating may be applied to smooth substrates, and may include a high level of fillers to provide increased scratch and damage resistance without compromising the above benefits.

In one form thereof, the present invention provides a single coat, non-stick coating system, including at least one binder resin (12), one binder resin including at least one of amide and amine functional groups; and at least one fluoropolymer resin (14a), one fluoropolymer resin capable of reacting with at least one of the amide and amine functional groups of the binder resin.

In another form thereof, the present invention provides a single-coat, non-stick coating system in the form of an aqueous dispersion, including a binder resin (12) including at least one of polyamideimide, polyamide, and polyimide; and a fluoropolymer resin (14a) including a copolymer of tetrafluoroethylene, hexafluoropropylene and vinylidene fluoride monomers.

In another form thereof, the present invention provides a substrate (16) coated with a single coat, non-stick coating, the non-stick coating including at least one binder resin (12), one binder resin including at least one of amide and amine functional groups; at least one fluoropolymer resin (14a), one fluoropolymer resin capable of reacting with at least one of the amide and amine functional groups of the binder resin; and a filler material.

BRIEF DESCRIPTION OF THE DRAWINGS

The above-mentioned and other features and advantages of this invention, and the manner of attaining them, will become more apparent and the invention itself will be better understood by reference to the following description of an embodiment of the invention taken in conjunction with the accompanying drawings, wherein:

BRIEF DESCRIPTION OF THE DRAWINGS

The above-mentioned and other features and advantages of this invention, and the manner of attaining them, will become more apparent and the invention itself will be better understood by reference to the following description of an embodiment of the invention taken in conjunction with the accompanying drawings, wherein:

Fig. 1 is a schematic illustration of a substrate surface having a known coating composition adhered thereto, and a topcoat adhered to the coating;

Fig. 2 is a schematic illustration showing a substrate having a single coat, non-stick coating system in accordance with the present invention adhered thereto, and further showing a topcoat adhered to the coating system;

Fig. 3 is a perspective view of a test apparatus for carrying out the mechanical scratch adhesion test of Test Method A, which is set forth in Appendix A;

Fig. 4 is a perspective view of an apparatus for carrying out the resistance to mechanical damage by knife cutting and scraping test of Test Method B, which is set forth in Appendix B; and

Fig. 5 is a schematic illustration showing the cutting and scraping action of a blade of the testing apparatus of Fig. 4 upon a substrate surface.

Corresponding reference characters indicate corresponding parts throughout the several views. The exemplifications set out herein illustrate preferred embodiments of the invention, and such exemplifications are not to be construed as limiting the scope of the invention in any manner.

DETAILED DESCRIPTION

The present invention provides a single coat non-stick coating system. The single coat system includes a fluoropolymer, which is a polymer including a $\text{CF}_2\text{-CH}_2$ moiety in the polymer chain. An exemplary fluoropolymer is a fluoropolymer copolymer, such as a fluoropolymer terpolymer including three repeating monomer units, specifically, each of tetrafluoroethylene ("TFE"), hexafluoropropylene ("HFP"), and vinylidene fluoride ("VDF") units. Fluoropolymer copolymers including TFE, HFP, and VDF monomers are collectively referred to as "THV". One suitable THV terpolymer is Dyneon® E-15851, available from Dyneon LLC, 8744 33rd Street North, Oakdale, MN., 55128, a 3M Company. (Dyneon® is a registered trademark of Dyneon LLC).

Further examples of such fluoropolymers are polyvinylidene fluoride ("PVDF") homopolymers, ethylene tetrafluoroethylene ("ETFE") and HFP/VDF bipolymers, ethylene fluorinated ethylene-propylene ("EFEP") terpolymers, and other possible combinations of ethylene and fluoroethylenic monomers.

The fluoropolymer may have a melting point of about 220° C or above, however, fluoropolymers having melting points between about 160° C and about 250° C are also suitable.

The present non-stick coating system may be applied to a wide variety of substrates, including but not limited to, metal cookware, printer and photocopier rollers, building materials, industrial tools, and high temperature resistant fabrics such as fiberglass and woven polyaramids.

Improving the connection between the binder and the fluoropolymer allows for sufficient stratification in the coating between the binder and fluoropolymer for improved substrate adhesion and release property, yet also allows the retention of the intracoat cohesion between the binder and fluoropolymer within the coating. Improving such connection may be accomplished by: (1) improving the wetting of the fluoropolymer by the binder, and (2) by creating a chemical bond, as opposed to a mechanical interconnection, between the binder and the fluoropolymer.


The present inventors have found that the addition of the THV terpolymer to a single coat composition including a binder provides a coating having excellent substrate adhesion and release properties and which is resistant to separation failure between the fluoropolymer and binder components. It is believed that THV accomplishes these improvements because (1) the VDF monomer in the THV terpolymer provides a slight increase in the surface energy of the fluoropolymer to thereby increase the wetting and adhesive contact with the binder, as demonstrated in Examples I, II(A), and II(B), and (2) the VDF monomer provides a reactive site that creates a chemical bond between the THV terpolymer and binder resins which include terminal amine and amide groups.

Regarding (1) above, the ability for the fluoropolymer and binder to be wetted onto one another, such that the binder and fluoropolymer are in intimate adhesive contact, is a function of the surface energies of the binder and fluoropolymer. Ideally, the surface energies of the binder and the fluoropolymer are substantially equal, to maximize the wetting therebetween. Because fluoropolymers have low surface energies (typically less than 25 dynes/cm), a significant difference in surface energies typically exists between the binder and

the fluoropolymer, inhibiting the wetting therebetween. It is believed that the VDF monomer in the THV terpolymer provides a slight increase in the surface energy of the THV terpolymer, which in turn provides a corresponding decrease in the difference in surface energies between the THV terpolymer and the binder to improve the wetting therebetween, as demonstrated in Examples I, II(A), and II(B).

In fact, as shown in Examples I, II(A), and II(B), the improved wetting between THV and the binder resin provides such sufficient attachment therebetween that a single coat non-stick coating composition including THV demonstrates superior substrate adhesion, release properties, and intracoat cohesion to known compositions, even without a binder which does not include terminal amine or amide groups, such as polyether sulfone ("PES"). The benefit of including THV in a coating composition having a binder with terminal amine or amide groups is described below.

Regarding (2) above, the ability of THV to form chemical bonds with terminal amine and amide groups increases the intracoat cohesion between THV and binders which include terminal amine and amide groups, such as polyamideimide ("PAI"). This type of bonding is illustrated by the well known chemistry associated with the vulcanization of THV elastomeric polymers, such that described in literature available from the 3M Company for use with its Fluorel® Fluoroelastomers. (Fluorel® is a registered trademark of Minnesota Mining and Manufacturing Co.). For example, such polymers undergo chemical crosslinking with diamines by the following reactions:



The amine functionality shown above in reactions (1) and (2) for terminal amine groups is also available for the amide groups of the PAI resin.

This improved intracoat cohesion in a primer for a multicoat system, which primer includes the THV terpolymer and a binder having terminal amine and amide groups, is schematically illustrated in Fig. 2, wherein a large degree of stratification between binder 12 and fluoropolymer 14a, which includes THV, is allowed, to maximize primer-substrate and primer-topcoat adhesion, while maintaining strong intracoat cohesion within primer 22a

between binder 12 and fluoropolymer 14a via the chemical bonding between binder 12 and fluoropolymer 14a, shown at 20a.

The fluoropolymers may comprise approximately 15 to 60% by weight of the solid content of the coating composition, wherein approximately 5 to 100% by weight of the fluoropolymers are capable of reacting with the amide and amine functional groups of the binder resin. Such fluoropolymers may have a melt viscosity of 10^3 to 10^6 poise. Additionally, the fluoropolymer capable of reacting with the amide and amine functional groups of the binder resin may include 5-30% by weight vinylidene fluoride ($-\text{CH}_2\text{-CF}_2-$) therein. The foregoing fluoropolymers may also be blended with other fluoropolymers such as polytetrafluoroethylene ("PTFE"), fluorinated ethylenepropylene ("FEP") and perfluoroalkyl ("PFA").

Binder resins may include polyester, polyamide, polyamideimide, polyimide, polyether sulfone, polyphenylene sulfide, polyether ether ketone, silicone, epoxy, and acrylic resins, and blends of the foregoing. The binder resins comprise approximately 25 to 65% by weight of the solid content of the coating composition, and approximately 20 to 100% by weight of the binder resin may include a resin with amide and/or amine functional groups.

Fillers may include inorganic metal oxides and metal oxide complexes, such as titanium dioxide, chromium dioxide, zinc oxide, iron oxide, aluminum oxide, silicon oxides, zirconium oxide, and mixtures of the foregoing; silicates, such as aluminum silicate, magnesium aluminum silicate, and mixtures of the foregoing; and inorganic carbides and nitrides, such as silicon carbide, titanium carbide, silicon nitride, titanium nitride, and boron nitride, and mixtures of the foregoing.

Pigments may include ultramarine blue zeolite, channel black, carbon black, and mixtures of the foregoing. The pigments and fillers may comprise from 0 to 45% by weight of the solid content of the coating composition.

The substrate may consist, for example, of stainless steel, carbon steel, or aluminum, which is smooth or which has been chemically etched or mechanically roughened by gritblasting or abrasion with grit impregnated pads, cloth, or paper to an average surface roughness of $0.5\text{ }\mu\text{m}$ to $2\text{ }\mu\text{m}$ (20-80 microinches) Ra, or alternatively, $2\text{ }\mu\text{m}$ to $5\text{ }\mu\text{m}$ (80-200 microinches) Ra.

EXAMPLES**Example 1****Comparison of damage resistance between coatings having varying proportions of THV and PTFE fluoropolymer resins.**

Mixtures of high temperature resistant organic binders with fluoropolymers and fillers were prepared, with the binders and fluoropolymers present at a fixed ratio with respect to each other. The mixtures were prepared from a base containing an aqueous solution of polyamide imide resin into which had been dispersed by ball milling a polyethersulfone ("PES") resin, as well as pigments and fillers including finely divided alumina, ultramarine blue and carbon black pigments. To this base was added in varying proportions an aqueous dispersion of PTFE and an aqueous dispersion of THV fluoropolymer terpolymer resin containing reactive vinylidene fluoride monomers. The coatings were formulated in such a way that the total amount of fluoropolymer to other ingredients was held constant while the ratio of one fluoropolymer to the other was varied. The composition of the solid ingredients in the coatings by weight was as follows:

Table I**Formulations of coatings with varying proportions of PTFE and THV.**

Coating Number	1	2	3	4	5	6
Polyamideimide resin	22	22	22	22	22	22
Polyethersulfone resin	6	6	6	6	6	6
Polytetrafluoroethylene resin	42	40	38	33	16	0
Terpolymer of TFE/HFP/VdF	0	2	4	9	26	42
Carbon Black pigment	2	2	2	2	2	2
Aluminum Oxide (Fine Particle Size)	15	15	15	15	15	15
Zinc Oxide	1	1	1	1	1	1
Ultramarine Blue pigment	12	12	12	12	12	12
Total	100	100	100	100	100	100

Test panels were prepared for each coating using 7" X 7" X 0.063" panels of 3003 aluminum alloy. The test panels were prepared by chemically cleaning and etching in a commercial dishwasher. The panels were exposed first to one six minute washer cycle using a

solution of 5% sodium hydroxide at ~65° C, followed by a deionized water rinse and a second six minute cycle using 1% nitric acid at ~65° C, followed by a deionized water rinse and drying. This treatment produced a clean, smut-free surface with an average roughness of ~30 microinches (0.75 micron).

Each coating was applied to a respective panel by spraying to a dry film thickness of 15 – 20 µm, and was cured for 5 minutes at 400°C metal temperature. The panels were tested for 30 minutes using the mechanical scratch tester as described in Test Method A, as set forth in Appendix A. The results were as follows:

Table II

Mechanical scratch test results of the coatings of Table I.

Coating Number	1	2	3	4	5	6
Scratch adhesion result, 10 = best	1	4.5	5	5.5	4.5	4

The results indicate that even a small amount of the THV terpolymer improves the damage resistance of the coating.

Example II(A)

Comparison of binder-fluoropolymer intracoat cohesion between coating compositions respectively containing FEP and THV fluoropolymers.

Two coating compositions were prepared, each including a binder of polyether sulfone ("PES") dissolved in N-methyl pyrrolidone and xylene. In one, fluorinated ethylene-propylene ("FEP") powder was dispersed, and in the other, a powder of THV terpolymer was dispersed, both at a ratio of 75% PES and 25% fluoropolymer by weight. The coatings were colored equally with an inorganic pigment as an aid to inspection. The coatings were then sprayed onto respective aluminum panels to a dry film thickness of 20 microns, and then cured for 5 minutes at 400° C.

Mixtures of polyethersulfone (PES) resin were prepared with an inorganic pigment and either: (1) a powder form of a fluorinated ethylenepropylene "FEP" fluoropolymer (a copolymer of tetrafluoroethylene and hexafluorofluoropropylene) or (2) a powder form of the THV fluoropolymer terpolymer described above. The mixtures were made by dissolving the PES resin in a blend of N-methylpyrrolidone and xylene and dispersing a mixed metal oxide green pigment (Shephard #223 Green) into the resin solution by bead milling. The two

powders were added by mixing and bead milling to achieve a suitable dispersion and smoothness. The composition of the solid ingredients in the two mixtures by weight was as follows:

Table III

Formulations of coatings with varying proportions of FEP and THV.

Coating Number	1	2
PES	42	42
FEP	0	33
Terpolymer of TFE/HFP/VdF	33	0
Inorganic Green pigment	25	25
Total	100	100

The mixtures were sprayed onto aluminum "Q" Panels, prepared as described above in Example I, to a dry film thickness of 20 μm and cured 5 minutes at 400°C.

On inspection, the coating containing FEP had a heavy waxy surface layer that could be removed with a fingernail down to a glossy lower layer. This indicated a sharp separation/stratification of the organic binder and FEP, as well as a loss of intracoat cohesion between the binder and fluoropolymer within the dried film. In contrast, the coating with the terpolymer fluoropolymer resin showed no removable waxy surface layer and excellent intracoat cohesion between the binder and fluoropolymer. This observation demonstrates the improved compatibility of the terpolymer resin compared to a higher fluorinated, but non-reactive fluoropolymer resin.

Example II(B)

Comparison of amount of fluoropolymer present at the surface thereof, between coating compositions respectively containing FEP and THV fluoropolymers.

In a second experiment, one coated panel was prepared using each of the above coatings in the manner described above in Example II(A). A cyanoacrylate glue was applied between the coated panels. The panels were clamped together for several minutes to cure the glue, and after curing the panels were forced apart. The glue completely released from the coating containing the terpolymer fluoropolymer resins, while glue residue was observed remaining on the surface of the FEP-containing coating. This result indicates that the amount of fluoropolymer at the surface of the terpolymer resin coating was equal to or greater than the

amount of fluoropolymer at the surface of the FEP coating and the release properties of the former were superior to the latter.

Example III

Preparation and physical testing of coating compositions respectively containing FEP and THV fluoropolymers used as primer.

Primers were prepared using mixing processes typical of coatings manufacturing operations. An aqueous solution of Torlon AI-10, polyamide imide resin, was first prepared by dissolving the resin in a mixture of N-methyl pyrrolidone ("NMP"), furfuryl alcohol, dimethylamine ethanol ("DMAE"), and wetting agents/surfactants in water, in a manner similar to that described in U.S. Patent No. 4,049,863 to Vassiliou. Fillers were dispersed in this solution, and two portions of the solution were then blended with respective aqueous dispersions of the FEP and THV fluoropolymers. The primer formulations are set forth in Table IV below, which table sets forth the composition of the "wet", or liquid phase, primer before application of the primer to the substrate followed by curing:

Table IV

Formulations of primers respectively including THV and FEP.

	Primer 1	Primer 2
Binder Resins:		
Torlon AI-10 Polyamideimide Resin	7.5	7.5
Fluoropolymers Resins:		
Daikin D-3B Polytetrafluoroethylene Dispersion	6.6	6.6
Dyneon THV E-15851 Dispersion	3.4	-
Daikin ND-1 FEP Dispersion	-	3.4
Other Solid Ingredients		
Norton E-330 Aluminum Oxide (Alumina)	4.0	4.0
Ferro RB-30 Ultramarine Blue Pigment	2.7	2.7
Zinc Oxide	0.1	0.1
Channel Black Pigment	1.0	1.0

Other		
Water	66.0	66.0
NMP	4.0	4.0
Furfuryl alcohol	1.5	1.5
DMAE	1.5	1.5
Air Products Surfylol 440	1.0	1.0
Triton X-100	0.7	0.7
Total	100.0	100.0

Rolled aluminum (alloy 1100) disks, ~ 7" in diameter and 0.635" thick, were prepared by chemically cleaning and etching in a commercial dishwasher. The disks were exposed first to one six minute washer cycle using a solution of 5% sodium hydroxide at ~ 65°C, followed by a deionized water rinse and a second 6 minute cycle using 1% nitric acid at ~ 65°C, followed by a deionized water rinse and drying. This treatment produced a clean, smut-free surface with an average roughness of ~30 microinches (0.75 micron). The primer compositions given as Primer 1 and Primer 2 above were sprayed onto respective ones of the disks. The primers were applied to a dry film thickness of 8 - 10 microns and dried for 2 minutes at 95°C to produce a coating that was dry to the touch.

Following drying, a topcoat of a composition similar to that described in U.S. Patent No. 4,049,863 to Vassiliou was sprayed onto the disks at a dry film thickness of 18 - 20 microns. The disks were dried for 2 minutes at 95°C, and cured for 5 minutes at 430°C to produce a smooth, glossy black non-stick coating.

The disks were subject to various tests to evaluate the adhesion and durability of the coating systems. Disks with both Primer 1 and Primer 2 had excellent resistance to knife scratching and excellent adhesion when subjected to cross hatching and boiling in water for 15 minutes.

Further, both had similarly good scratch resistance when evaluated by a mechanical scratch tester as described in Test Method A, as set forth in Appendix A hereto. Test method A simulates the scratching action of a fork, and is a measure of resistance of the coating to penetration by a sharp point.

However, there were significant differences found when the disks were evaluated by a mechanical knife scratch tester as described in Test Method B, as set forth in Appendix B

hereto. Test method B simulates the scraping action of a spatula and the cutting action of a knife blade, wherein ratings may be applied thereto based on the observed results (which ratings are set forth in Test Method A). In this test, a significant portion of the topcoat applied over Primer 2 was scraped off, resulting in a rating of about 6, while the topcoat applied over Primer 1 remained almost entirely intact, resulting in a rating of about 9. This demonstrates both (1) the improved adhesion between Primer 1 and the topcoat (intercoat adhesion) and (2) the improved cohesion within the Primer 1 itself (intracoat cohesion) over Primer 2, where Primer 1 includes the THV and Primer 2 includes FEP.

Example IV

Preparation and physical testing of a coating composition containing THV, and a combination of polyamideimide and polyether sulfone resins, wherein the coating is used as primer.

A primer composition including THV was prepared in accordance with the procedure set forth in Example III above, wherein part of the polyamideimide organic binder resin was replaced with polyether sulfone. The primer formulation is set forth in Table V below, which table sets forth the composition of the "wet", or liquid phase, primer before application to a substrate followed by curing:

Table V

Formulation of a primer containing THV and a combination of polyamideimide and polyether sulfone resins.

Examples		Primer 3
Binder Resins:		
	Torlon AI-10 Polyamideimide Resin	6.0
	Radel A700X Polyether Sulfone Resin	1.5
Fluoropolymers Resins:		
	Daikin D-3B Polytetrafluoroethylene Dispersion	6.6
	Dyneon THV E-15851 Dispersion	3.4
	Daikin ND-1 FEP Dispersion	-
Other Solid Ingredients		
	Norton E-330 Aluminum Oxide (Alumina)	4.0

	Ferro RB-30 Untramarine Blue Pigment	2.7
	Zinc Oxide	0.1
	Channel Black Pigment	1.0
	Other	
	Deionized water	66.0
	N-methyl pyrrolidone (NMP)	4.0
	Furfuryl alcohol	1.5
	Dimethylamino ethanol (DMAE)	1.5
	Air Products Surfylol 440 (surfactant)	1.0
	Triton X-100 (surfactant)	0.7
	Total	100.0

Prior to adding to the formula, the polyether sulfone resin was ground by ball milling for 72 hours in a water slurry until it was reduced in particle size to less than 15 microns average. The above primer formula was coated onto aluminum disks prepared as described above in Example III, and a topcoat was applied thereto, again as described above in Example III. The resulting coating system including Primer 3 had adhesion and scratch resistance, as measured by Test Methods A and B, respectively, which were superior to Primer 1, and additionally, Primer 3 had better flexibility than Primer 1.

Although several broad examples which incorporate the present invention have been described above, it is to be understood that the present invention is not to be limited by the examples disclosed herein. Indeed, the disclosure and examples above teach one of ordinary skill a virtually limitless number of conditions which would be within the scope of the claims appended hereto.

Further, while this invention has been described as having a preferred design, the present invention may be further modified within the spirit and scope of this disclosure. This application is therefore intended to cover any variations, uses, or adaptations of the invention using its general principles. Further, this application is intended to cover such departures from the present disclosure as come within known or customary practice in the art to which this invention pertains and which fall within the limits of the appended claims.

application is therefore intended to cover any variations, uses, or adaptations of the invention using its general principles. Further, this application is intended to cover such departures from the present disclosure as come within known or customary practice in the art to which this invention pertains and which fall within the limits of the appended claims.

APPENDIX A

Test Method A

Mechanical Scratch Adhesion

1. Scope:

Coatings for cookware are susceptible to abuse and damage by scratching and cutting with metal utensils. Resistance to this kind of damage is often measured by a so called "Tiger Paw" test. In this test, a device equipped with ball point pen tips is used to stir food cooking in a piece of coated cookware. The pen points simulate damage by metal utensils, and provide a convenient renewable test implement. However, the "Tiger Paw" test is long in duration, difficult to control and subjective to evaluate.

Test Method A describes a procedure and apparatus that inflicts similar abuse on coatings, yet is reproducible, objective and quick. As shown in Fig. 3, test apparatus 30a includes weighted ball point pen tip 32 affixed to balance arm 34, where pen tip 32 is placed on coated substrate surface 36 which is revolving on turntable 38. At the same time, balance arm 34 oscillates from side to side by means of revolving cam 40. Turntable 38 and cam 40 are driven by constant speed DC motors 42. The speed of turntable 38 and cam 40 are controlled by variable DC power supplies. The amplitude of oscillation is controlled by the degree of eccentricity in cam 40. Weight 44 is variable. By adjusting the speeds of motors 42 and the amplitude of oscillation of balance arm 34, various scratch patterns may be obtained. These can be adjusted to cover a small or large surface area.

To further simulate the conditions encountered by coatings for non-stick cookware, test piece 50 (panel or pan) is covered with hot oil 51. The temperature of oil 51 is maintained with IR heat lamps 52 and is monitored with a thermometer or thermocouple (not shown).

2. Equipment and Materials:

- 2.1 Mechanical scratch adhesion apparatus 30a with set of weights 44.
- 2.2 Ball point pen tip 32, such as Paper Mate medium point standard refill cartridges or equivalent.
- 2.3 Hot plate
- 2.4 Cooking oil 51
- 2.5 Thermometer or digital read out with thermocouple wire
- 2.6 Small clips 53

- 2.7 Shallow pan approximately 10 inches (25 cm) in diameter.
- 2.8 Set (2 or 3) of 250 watt infrared heating lamps 52 on stands.

3. Procedure:

- 3.1 Check the balance and level of balance arm 34 with test piece 50 in position. Adjust if necessary. Remove test piece 50. Set the amplitude of the oscillation by choosing the proper cam setting. Set the minimum and maximum radius by loosening the balance arm retaining screw (not shown) and adjusting at the extremes of cam 40. Usually, a center circle of about 2 inches is allowed in the test pattern.
- 3.2 Without weight on balance arm 34, and holding pen 32 above turntable 38, adjust the speed of turntable 38 and cam 40. Typically, cam 40 moves at a rate of 0 to 3 times faster than turntable 38.
- 3.3 Place a piece of paper on turntable 38 and hold in place with tape. Load pen 32 with a light weight 44 (approx. 200 grams.) Place pen 32 on the paper and allow to trace the scratch pattern it will follow. Save the pattern. This is also a check of the functioning of pen 32. If pen 32 does not write, replace it.
- 3.4 Remove paper. Center test piece 50 on turntable 38. (If testing panels (not shown), place test piece 50 on turntable 38 and place panels in test piece 50. Panels must be of a size large enough to accommodate the size of the scratch pattern). Using clips 53, anchor test piece 50 to turntable 38. Holding pen 32 above test piece 50, turn on turntable 38 and cam 40 and observe several revolutions to ensure that the scratch pattern is entirely on test piece 50. Turn off motor 42.
- 3.5 Heat sufficient cooking oil 51 to cover test surface by about 1/4 inch. Heat to test temperature. (CAUTION: Above about 150°C, cooking oils 51 emit fumes and strong odors. Also, they become quite flammable. If running over 150°C, conduct test in a well ventilated area, preferably in a fume hood.) Pour hot oil 51 into test piece 50. Position IR lamps 52 close to test piece 50 and turn on to maintain temperature of oil 51. Some pre-testing of the proper position of lamps 52 will be required to maintain the temperature within a range of $\pm 5^{\circ}\text{C}$. Monitor every 5 minutes during test, and adjust position of lamps 52 to hold

this tolerance. (A continuously reading temperature gauge is most convenient for this measurement.)

- 3.6 Place a proper weight 44 on balance arm 34. Typically, this will vary from 250 to 1000 grams. Start both motors 42 and place pen 32 gently on coated surface 36. Allow the test to run for the required length of time.

4. Evaluation:

- 4.1 Record the following information: (1) speed of turntable 38 and cam 40 in rpm; (2) cam amplitude setting (number or distance from inside to outside radius in cm); (3) load on pen point 32 in grams; (4) temperature of oil 51; (5) duration of test; and all test piece parameters (substrate and substrate preparation, coating, thickness, cure, etc.).
- 4.2 Remove test piece 50, drain oil 51, and wash in warm water and mild detergent. Blot dry with paper towel. Visually observe the damage to the coating surface 36. This may be done on a comparative basis against other test specimens, or may be rated on the scale set forth below. In general, performance levels have been rated as follows:

Table VI

Performance levels

10	No effect	Light scratching of the surface. No break through at any place in the scratch pattern.
8	Slight	Light scratching of the surface. Inner circle of pattern is cut through to metal 100%. Outer circle cut through to metal <50%.
6	Moderate	Moderate scratching between inner and outer circle. Inner and outer circle both cut through to metal (inner usually worse than outer.) At this point begin inspecting and noting adhesion loss between coats or to substrate.
4	Considerable	Less than 25% loss of coating between inner and outer circuit. (Estimate and record amount.) Considerable cut through and fraying at the inner and outer circles.
2	Severe	Between 25% to 50% loss of coating between inner and outer circle. Severe loss of coating at inner and outer circles. Metal substrate quite apparent.
0	Total Failure	Greater than 50% loss of adhesion and coating surface.

5. Comments and Precautions:

- 5.1 The preferred approach to running this test is to establish a set of operating parameters for speeds of turntable 38 and cam 40, the oscillating amplitude, and temperature of oil 51, then vary the load or time. Once this has been established, setting up individual tests proceeds quickly and smoothly.
- 5.2 Check balance arm 34 and oscillation of balance arm 34 frequently to ensure that it has not become loose and changed.
- 5.3 This test can be run cold, i.e., without hot oil 51.

APPENDIX B

Test Method B

Resistance to Mechanical Damage by Knife Cutting and Scraping

1. Scope:

This test simulates the cutting and scraping action of metal kitchen utensils on a non-stick coated surface. It measures the resistance to slicing through the coating by the edge of a blade as well as resistance to sideways scraping by a blade. Therefore, the test is a good indicator of resistance to damage by kitchen utensils such as metal spatulas. The test is very reproducible, and readily distinguishes differences in the hardness, toughness and adhesion (especially intercoat adhesion) of coatings systems.

2. Equipment and Materials:

- 2.1 Mechanical scratch adhesion apparatus 30b, such as that shown in Fig. 4, with set of weights 44 and fixture arm 60 to hold blade 62 at a proper angle to coated substrate surface 36b.
- 2.2 Steel Q-Panel blades 62 (Type QD-35), available from Q-Panel Company.
- 2.3 Timer.

3. Procedure:

- 3.1 Position test piece 64 on the center of turntable 38 of scratch adhesion apparatus 30b.
- 3.2 Lock a new Q-Panel blade 62 into place in fixture arm 60. Make sure that panel blade 62 is in the position shown in Fig. 4.
- 3.3 Load fixture arm 60 with weight 44. Typically, this weight is between 750 to 1,000 g. A standard weight 44 is 900 g. Lock fixture arm 60 so that fixture arm 60 does not make contact with test piece 64.
- 3.4 Start turntable 38. The speed should be 15 -16 rpm in an anti-clockwise direction. Start cam 40 to oscillate fixture arm 60. The cam speed should be 20 - 22 rpm. Release fixture arm 60 and set the edge of panel blade 62 gently on substrate surface 36b of test piece 64.
- 3.5 Continue running the test until an agreed upon endpoint is reached. Usually, this test is run for two hours or until 10% of the substrate is revealed.

4. Evaluation:

- 4.1 Refer to Fig. 5. This drawing shows the motion of test piece 64 at 70 and the motion of panel blade 62 at 72.
- 4.2 Rate the amount of wear at Points A, B, and C according to the scale set forth in Table III of Test Method A. The area between A and B receives single scraping action at maximum circumferential speed. Panel blade 62 is perpendicular to the circle of rotation of test piece 64. Circle A receives the second greatest scraping damage. The area between B and C receives double scraping action at medium to low circumferential speed. Circle B receives the greatest scraping action. Circle C receives cutting action with panel blade 62 running tangential to the circle of rotation of test piece 64.
- 4.3 Photograph results.
- 4.4 If running a series of tests it is sometimes easier to rank the performance to provide a relative rating of damage resistance rather than an absolute number rating. Wear patterns can vary, and a single numerical rating does not always convey the true nature of the damage resistance of the coating.

WHAT IS CLAIMED IS:

1. A single coat, non-stick coating system, comprising:
at least one binder resin (12), one said binder resin including at least one of amide and amine functional groups; and
at least one fluoropolymer resin (14a), one said fluoropolymer resin capable of reacting with at least one of said amide and amine functional groups of said binder resin.
2. The coating system of Claim 1, wherein one said binder resin is selected from the group consisting of polyamideimide, polyamide, polyimide, and a combination thereof.
3. The coating system of Claim 2, further including an additional resin selected from the group consisting of polyphenylene sulfide, polyether sulfone, polyether ether ketone, silicone, and a combination thereof.
4. The coating system of Claim 1, wherein said fluoropolymer resin (14a) includes an additional fluoropolymer resin selected from the group consisting of polytetrafluoroethylene, fluorinated ethylene propylene, perfluoroalkyl, and a combination thereof.
5. The coating system of Claim 1, wherein said fluoropolymer resin (14a) is a copolymer including vinylidene fluoride monomers.
6. The coating system of Claim 1, wherein said fluoropolymer resin (14a) is a terpolymer of tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride, having a melting point of from about 160° C to about 250° C.
7. The coating system of Claim 1, wherein said binder resin (12) comprises approximately 25% to 65% of the solid content of said coating system.
8. The coating system of Claim 1, wherein said binder resin (12) comprises approximately 20% to 100% by weight a resin including a functional group selected from the group consisting of amide and amine functional groups.
9. The coating system of Claim 1, wherein said fluoropolymer resin (14a) comprises approximately 15% to 60% by weight of the solid content of the coating system.
10. The coating system of Claim 1, wherein said fluoropolymer resin (14a) comprises approximately 5 to 100% by weight of the solid content of the coating system a fluoropolymer resin with vinylidene fluoride moiety.
11. The coating system of Claim 1, wherein said fluoropolymer resin (14a) comprises 5% to 30% by weight vinylidene fluoride.

12. The coating system of Claim 1, wherein said fluoropolymer resin (14a) has a melting point in the range of about 160° C to about 250° C.

13. The coating system of Claim 1, wherein said fluoropolymer resin (14a) has a melt viscosity of greater than about 10³ poise.

14. The coating system of Claim 1, further including a filler material selected from the group consisting of zinc oxide, aluminum oxide, zirconium oxide, titanium dioxide, iron oxide, chromium dioxide, silicon oxide, aluminum silicate, magnesium aluminum silicate, silicon carbide, titanium carbide, silicon nitride, titanium nitride, boron nitride, and mixtures thereof.

15. The coating system of Claim 14, further including a pigment, said pigment selected from the group consisting of ultramarine blue zeolite, channel black, carbon black, and mixtures thereof.

16. The coating system of Claim 15, wherein said pigments and said fillers comprise approximately 0% to 45% by weight of said primer.

17. A single-coat, non-stick coating system in the form of an aqueous dispersion, comprising:

a binder resin (12) including at least one of polyamideimide, polyamide, and polyimide; and

a fluoropolymer resin (14a) including a copolymer of tetrafluoroethylene, hexafluoropropylene and vinylidene fluoride monomers.

18. The coating system of Claim 17, wherein said binder resin includes an additional resin selected from the group consisting of silicone, polyether sulfone, polyphenylene sulfide, polyether ether ketone, and a combination thereof.

19. The coating system of Claim 17, wherein said fluoropolymer resin (14a) includes an additional resin selected from the group consisting of polytetrafluoroethylene, fluorinated ethylene propylene, perfluoroalkyl, and a combination thereof.

20. The coating system of Claim 17, further including a filler material selected from the group consisting of zinc oxide, aluminum oxide, zirconium oxide, titanium dioxide, chromium dioxide, silicon dioxide, aluminum silicate, magnesium aluminum silicate, silicon carbide, titanium carbide, silicon nitride, titanium nitride, boron nitride, and mixtures thereof.

21. The coating system of Claim 17, further including a pigment selected from the group consisting of ultramarine blue zeolite, channel black, carbon black, and mixtures thereof.

22. A substrate (16) coated with a single coat, non-stick coating, said non-stick coating comprising:

at least one binder resin (12), one said binder resin including at least one of amide and amine functional groups;

at least one fluoropolymer resin (14a), one said fluoropolymer resin capable of reacting with at least one of said amide and amine functional groups of said binder resin; and
a filler material.

23. The substrate (16) of Claim 22, wherein one said binder resin (12) is selected from the group consisting of polyamideimide, polyamide, polyimide, and a combination thereof.

24. The substrate (16) of Claim 22, wherein said fluoropolymer resin (14a) includes a copolymer having tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride monomers

25. The substrate (16) of Claim 22, wherein said fluoropolymer resin (14a) includes an additional resin selected from the group consisting of polytetrafluoroethylene, fluorinated ethylene propylene, perfluoroalkyl, and a combination thereof.

26. The substrate (16) of Claim 22, wherein said coating is applied to said substrate by at least one of spraying, curtain coating, and roller coating.

27. The substrate (16) of Claim 22, wherein said substrate (16) is selected from the group consisting of stainless steel, carbon steel, and aluminum having a surface roughened to an average roughness of about 2 – 5 μm (80 – 200 microinch).

28. The substrate (16) of Claim 22, wherein said substrate (16) is aluminum etched to an average roughness of about 0.5 to 2 μm (80 – 200 microinch).

29. The substrate (16) of Claim 22, wherein said filler material is selected from the group consisting of zinc oxide, aluminum oxide, zirconium oxide, titanium dioxide, chromium dioxide, silicon dioxide, aluminum silicate, magnesium aluminum silicate, silicon carbide, titanium carbide, silicon nitride, titanium nitride, boron nitride, and mixtures thereof.

30. The substrate (16) of Claim 22, wherein said coating further includes a pigment, said pigment selected from the group consisting of ultramarine blue zeolite, channel black, carbon black, and mixtures thereof.

10




FIG. 1
PRIOR ART




FIG. 2






FIG. 3



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US01/41761

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : B32B 15/08, 27/18, 27/30, 27/34; C08L 27/12, 77/00
US CL : 428/421, 422, 473.5, 474.4; 524/430, 506, 508, 514; 525/178, 179, 180

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
U.S. : 428/421, 422, 473.5, 474.4; 524/430, 506, 508, 514; 525/178, 179, 180

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
Please See Continuation Sheet

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ---	US 5,667,846A (THOMAS) 16 September 1997 (16.09.1997), abstract, tables, claims.	1-4,7-10,12-23,25-30
Y		5,6,11,24
X ---	US 5,709,949A (CHEN et al) 20 January 1998 (20.01.1998), abstract, claims.	1-4,7-10,12-23,25-30
Y		5,6,11,24

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"B" earlier application or patent published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

19 November 2001 (19.11.2001)

Date of mailing of the international search report

06 DEC 2001

Name and mailing address of the ISA/US

Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703)305-3230

Authorized officer

Ana L. Woodward

Jean Proctor
Paralegal Specialist

Telephone No. (703) 305-8183

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US01/41761

Continuation of B. FIELDS SEARCHED Item 3:

WEST search terms: polyamideimide, polyamide, polyimide, fluoropolymer, fluororesin, vinylidene fluoride, filler, pigment, binder, aqueous, multilayered, polyphenylene sulfide, polyether sulfone, polyether ether ketone, silicone